

TEKNOBRUSH 6600-00

Topcoat

TEKNOBRUSH 6600-00 is a water-borne topcoat for the repair of industrial treated wood designated for exterior use such as windows and doors. For surfaces treated with AQUATOP 2600.



TECHNICAL DATA

Fields of application	Exterior doors, Windows
Recommended substrate	Hardwood, Softwood
Volatile organic compound (VOC)	Approx. 39 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Colours	Base 1, 2 and 3 (white and opaque colours).
Tinting system	Teknolor
Gloss (60°)	Semi-matt
Thinner	The product is delivered ready for use.
Storage	Storage temperature is +5°C - +30°C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.
Packaging	2.7 l.

DIRECTION FOR USE

Surface preparation	The wood must be free from wood dust and contamination. The moisture content of the wood should be approx. 13% and should not exceed 15%.
Application method	Brush
Application conditions	Stir thoroughly before use. Optimum temperature for products and surroundings: +18°C - +22°C. Optimum relative air humidity: Approx. 50%. Film thickness: Approx. 75 µm wet.
Drying time	+20°C / 50% RH
- dry to handle	1-2 h
- fit for sanding and overcoating	3-4 h The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation, and film thickness.
Cleaning	Water.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.