



Q 99-280

2K Elastic Additive

Characteristics

99-280 Additive used to improve the elasticity of Q-Refinish 2K car and 2K vehicle and 2K clearcoats, which are mixed in the ratio 2:1. This additive is required to paint deformable plastics.

Physical Characteristics



colourless



Basic paint + 10 - 50 % 99-280 2K Elastic Additive

Processing conditions



Ensure an adequate supply and exhaust air ventilation.
Working temperature must be at least +10 °C. Max. air humidity 80 %.

Processing tips



The addition 99-280 2K Elastic Additive does not affect the quantity of the hardener to be added. Depending on the added quantity of 99-280 2K Elastic Additive, the drying time is extended up to 100%.

Storage



Store the product in a ventilated place. Keep away from direct exposure to sunlight.
Keep between +5°C and 20°C.

Safety



For more informations check the safety data sheet.



This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.