

TEKNOCOAT AQUA 1879-03

Water-borne lacquer

Polyurethane magnified, water-borne lacquer. Surface treatment of floors, furniture, and other wooden substrates for indoor use.



Quick drying lacquer that provides a very wear resistant surface. Adhesion to certain plastic types like PVC.

FURNITURE TEST:

Comply with the demands in category 1, 2 and 3. The test of the surface varies with the colour. Separate test for furniture can be ordered.



TECHNICAL DATA

Fields of application	Furniture, Stairs, Floors
Recommended substrate	Hardwood, Softwood
Solids	Approx. 40% by weight
Total mass of solids	Approx. 422 g/l
Viscosity	50-60 s, DIN 4 at +20°C.
Volatile organic compound (VOC)	Approx. 55 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Tinting system	Teknocolor
Gloss (60°)	Semi-matt
Thinner	Water.
Density	Approx. 1.03 kg/l
Storage	Protected against frost and not above +30°C. The storage stability is shown on the label. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	The surface should be well smoothed to reduce rising of wood fibres. Previously painted surfaces should be properly mat sanded. The wood must be free from wood dust and contamination.
Application method	Mohair roller, Brush, Spray
Recommended amount to be applied	2 x 100 g/m ²
Application	Stir thoroughly before use.

Application conditions	Should not be applied or left to dry at temperatures below +18°C. For evaluation of ventilation please contact Teknos consultant. Used on dark woods, water-borne lacquers may show less "glow and depth" than solvent-borne lacquers. Wood containing tannin such as oak may result in smoke-tinting. Before final lacquering we recommend test lacquering and tape test.
Drying time	+20°C / 60% RH
- stackable	Approx. 2 h
- fit for sanding	Approx. 1 h
- forced drying	Min. +40°C / 60% RH: - stackable: approx. 45 min. - fit for sanding: approx. 30 min. The drying times are based on an amount applied of 100 g wet lacquer per m ² and efficient ventilation. After forced drying the objects should be cooled to +30°C before stacking.
Drying methods	Air- or oven drying.
Cleaning	Water, TEKNOCLEAN 1949-00.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.